

Specification video VT-18 Cr

N	Property	Unit	Value	
			VT-18 CrHG	VT-18 CrPG
1*	Luminance	dB	≥ 1,0	≥ 0,5
2*	Luminance signal-to-noise ratio, AM	dB	≥ 1,5	≥ 1,0
3*	Chrominance signal-to-noise ratio, AM	dB	≥ 1,0	≥ 1,0
4	Drop-out – 20dB/15 μs	min ⁻¹	£ 12	£ 20
5*	Sensitivity, 1 kHz	dB	≥ -2,0	≥ -2,0
6	Tape thickness	μ	18,0 ^{+0,0} _{-2,0}	18,0 ^{+0,0} _{-2,0}
7	Tape width	mm	12,65 ^{+0,01} _{-0,01}	12,65 ^{+0,01} _{-0,01}
8	Breaking strength	N	≥ 40	≥ 40
9	F 5%	N	≥ 20	≥ 20

* - Values are given with reference to VRT 2.

All properties measured in conformity with JVC standard under normal environment conditions:
humidity 65±5%, temperature 20±2 °C.

Specification video tape VT-19 Cr

N	Property	Unit	Value	
			VT-19 CrHG	VT-19 CrPG
1*	Luminance	dB	≈ 1,0	≈ 0,5
2*	Luminance signal-to-noise ratio, AM	dB	≈ 1,5	≈ 1,0
3*	Chrominance signal-to-noise ratio, AM	dB	≈ 1,0	≈ 1,0
4	Drop-out – 20dB/15 μs	min ⁻¹	£ 12	£ 20
5*	Sensitivity, 1 kHz	dB	≈ -2,0	≈ -2,0
6	Tape thickness	μ	19,0 ^{+1,0} _{-2,2}	19,0 ^{+1,0} _{-2,2}
7	Tape width	mm	12,65 ^{+0,01} _{-0,01}	12,65 ^{+0,01} _{-0,01}
8	Breaking strength	N	≈ 40	≈ 40
9	F 5%	N	≈ 24	≈ 24

* - Values are given with reference to VRT 2.

All properties measured in conformity with JVC standard under normal environment conditions:
humidity 65±5%, temperature 20±2 °C.